

Product data sheet



Product: MW98A
MIRO®White 98 (M16)
Substrate: Aluminum

4700/1171/004/06.25

Alloy	¹	99,0 or more pure
Hardness	²	./.

Treatment front side	(S1)	matt, highly diffuse reflective film laminated on aluminium substrate
----------------------	------	---

Dimensions			
Length	[mm]		+1,5/0,00
Metal Thickness	[mm]		0,48±0,04
Width up to	[mm]		<1220

Optical Values			
reflectance @ 550 nm	[%]		98±1
Brightness L*	[-]		99,0±1,0
Colour value b*	[-]		+0,7±0,5
Colour value a*	[-]		-0,2±0,5
Brightness 60° along	[-]		<1,0
Brightness 60° across	[-]		<1,0
Brightness 85° along	[-]		<1,0
Brightness 85° across	[-]		<1,0

¹ based on DIN EN 573-3 (Aluminium) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium) resp. Rolling mill standard

